



Technical data sheet - ASA REGSHARE filament	
Producer	REGSHARE s.r.o.
Material	ASA (2-Propenoic acid butyl ester polymer with ethenylbenzene and 2-propenenitrile) CAS: 26299-47-8
CLP	Material does not require classification according to Regulation (EC) 1272/2008
Weight	1 Kg (+/- 50 g)
Packaging	Vacuum packed in water, moisture and UV resistant packaging. The packaging is resealable.
Diameter	1.75 mm (+/- 0.05 mm)
Colour	white, black, orange, blue, green
Nozzle temperature	240-270 °C
Bed temperature	80-115 °C
Nozzle	No limitation
Viscosity	1.07 dl/g
Softening temperature	85 °C
Melting temperature	170 °C

